


# Technical Information Sheet



## APP 160 Cool

Item Description	Item Number
1 Roll (1 square)	W70PTT1600

## Description

APP 160 Cool is a smooth-surface APP modified bitumen membrane designed to be installed with Elevate All-Purpose MB Cold Adhesive. It consists of select asphalt, modified with atactic polypropylene, and strengthened with a fiber glass reinforced nonwoven polyester mat [190 g/m<sup>2</sup> (3.9 lb/100 ft<sup>2</sup>)] made with 100 % recycled PET fibers. The combination results in a flexible and durable material that exceeds the performance requirements of ASTM D 6222 Type I, Grade S. APP 160 Cool is strong and stable, and resistant to natural forces and other factors on the rooftop. It is ideal for both new construction and re-roofing applications as a base ply, cap sheet, or as a flashing sheet in single or multi-ply APP applications.

**NOTE:** Meets or exceeds performance requirements of ASTM D 6222, Type I, Grade S.

## Product Packaging

Property	Value	Property	Value
Roll Width	3 ft 3 in (1 m)	Pallet Size	48 x 39 in (1.2 x 1 m)
Roll Length	32 ft 10 in (10 m)	Rolls Per Pallet	20
Net Coverage	98 ft <sup>2</sup> (9.1 m <sup>2</sup> )	Weight per Pallet	2,140 lb (971 kg)
Roll Weight	107 lb (49 kg)		

## Method of Application

1. APP 160 Cool must be fully adhered with Elevate Multi-Purpose Cold Adhesive.
2. Please reference the Elevate Asphalt Roofing Systems Guide for Applicators and Designers available on our website for detailed information regarding the application of APP 160 Cool.

## Acceptable Immediate Substrates for Cold Adhesive Application

- Structural Concrete (must be clean, dry, properly cured, and primed with ASTM D-41 primer).
- Approved Elevate Base Sheet.
- Existing Smooth Surface BUR or APP Modified Bitumen (must be clean, smooth, and primed with ASTM D-41 primer).
- DensDeck® Prime, SECUROCK® Gypsum Fiber.
- ISO 95+™ GL Insulation, ISOGARD HD Composite or Cover Board, ISOGARD CG Insulation.

**NOTE:** Please reference the Elevate Asphalt Roofing Systems Guide for Applicators and Designers available on our website for detailed information regarding the type of deck and insulation in use.

## Storage

- All material should be stored out of the weather in a clean, dry area in its original unopened packaging at a minimum of 50 °F (10 °C) and a maximum of 100 °F (38 °C) so that it will be 50 °F (10 °C) or above at the time of application.
- Do not stack APP 160 Cool membrane more than two (2) pallets high.
- If the material must be stored temporarily on the roof before application, it must be elevated from the roof surface on a pallet, stored on end, and covered from the weather with a light-colored opaque tarp in a neat, safe manner that does not exceed the allowable load limit of the storage area.

## Precautions

- For safety information, refer to the Safety Data Sheet (SDS) for APP Membranes and Flashing.
- Take care when transporting and handling Elevate Modified Bitumen rolls to avoid punctures and other types of physical damage.
- Isolate waste products, petroleum products, grease, oil (mineral and vegetable) and animal fats from all Elevate Modified Bitumen membranes.
- Refer to Safety Data Sheets (SDS) for additional safety information.

## LEED® Information

Post-Consumer Recycled Content: 8 %  
 Post Industrial Recycled Content: 0 %  
 Manufacturing Location: Beech Grove, IN



**NOTE:** LEED® is a registered trademark of the U.S. Green Building Council

Typical Properties (Meets ASTM D1622, Type I, Grade S)			
Properties	Test Method	Performance Minimum	Typical Performance
Product Thickness:	D 5147	140 mil (3.5 mm)	155 mil (3.9 mm)
Net Mass:	D 146	70 lb/100 ft <sup>2</sup> (3,418 g/m <sup>2</sup> )	104 lb/100 ft <sup>2</sup> (5,078 g/m <sup>2</sup> )
Bottom Side Coating:	D 5147	30 mil (0.76 mm)	47 mil (1.20 mm)
Peak Load at 73 °F (23 °C):	D 5147	50 lbf/in, MD (8.8 kN/m, MD)	55 lbf/in, MD (9.6 kN/m, MD)
		50 lbf/in, XMD (8.8 kN/m, XMD)	55 lbf/in, XMD (9.6 kN/m, XMD)
Elongation at Peak Load at 73 °F (23 °C):	D 5147	23 %, MD	30 %, MD
		23 %, XMD	30 %, XMD
Peak Load at 0 °F (-18 °C):	D 5147	60 lbf/in, MD (10.5 kN/m, MD)	65 lbf/in, MD (11.4 kN/m, MD)
		60 lbf/in, XMD (10.5 kN/m, XMD)	65 lbf/in, XMD (11.4 kN/m, XMD)
Elongation at Peak Load at 0 °F (18 °C):	D 5147	10 %, MD	15 %, MD
		10 %, XMD	15 %, XMD
Ultimate Elongation at 5 % of Peak Load 73 °F (23 °C):	D 5147	30 %, MD	40 %, MD
		30 %, XMD	40 %, XMD
Tear Strength at 73 °F (23 °C):	D 5147, D 4073	70 lbf, MD (311 N, MD)	75 lbf, MD (334 N, MD)
		70 lbf, XMD (311 N, XMD)	75 lbf, XMD (334 N, XMD)
Low Temperature Flexibility:	D 5147	32 °F (0 °C)	32 °F (0 °C)
Dimensional Stability:	D 5147, D 1204	1 % Change, MD	0.2 % Change, MD
		1 % Change, XMD	0.2 % Change, XMD
Compound Stability:	D 5147	230 °F (110 °C)	270 °F (132 °C)
Water Absorption:	D 5147, D 95	3.2 %	0 %
Moisture Content:	D 5147, D 95	1 %	0 %
Low Temperature Unrolling:	D 5636	41 °F (5 °C)	0 °F (-18 °C)

Please contact Holcim Technical Services at 800-428-4511 for further information.

This sheet is meant to highlight Elevate products and specifications and is subject to change without notice. Holcim takes responsibility for furnishing quality materials that meet published Elevate product specifications or other technical documents, subject to normal manufacturing tolerances. Neither Holcim nor its representatives practice architecture. Holcim offers no opinion on and expressly refuses any responsibility for the soundness of any structure. Holcim accepts no liability for structural failure or resultant damages. Consult a competent structural engineer prior to installation if the structural soundness or structural ability to properly support a planned installation is in question. No Holcim representative is authorized to vary this disclaimer.