

Technical Information Sheet

Image Coming Soon

PVC Clear Cut Edge Sealant LVOC

Item Description	Item Number
16 oz. (0.47 L) squeeze bottles with applicator nozzles	W56PAC2001

Description

Elevate PVC Clear Cut Edge Sealant LVOC is an optional treatment used for sealing cut edges of PVC and PVC KEE membrane where scrim reinforcement is exposed.

Method of Application

1. Surfaces to receive PVC Clear Cut Edge Sealant LVOC must be clean, dry, and free of loose and foreign materials, oil, and grease.
2. Allow the welded seam to cool prior to application of PVC Cut Edge Sealant LVOC. Seam should be cool to the touch.
3. Clean seam area with Elevate Splice Wash SW-100 prior to treating the cut edge with sealant.
4. Trim the tip of the nozzle to provide approximately a 1/8" (3.2 mm) opening.
5. Apply an approximate 1/8" to 1/4" (3.2 mm to 6.4 mm) diameter bead of sealant to cut edges of Elevate PVC membrane with exposed reinforcement.

Coverage Rate

- 1/8" (3.2 mm) diameter bead: 1,500 ft/gal (121 m/L)
- 1/4" (6.4 mm) diameter bead: 400 ft/gal (32 m/L)

Storage

- Shelf life will be shortened if exposed to elevated temperatures.
- Store in original containers.

Shelf Life

Shelf life of one year can be expected if stored in original sealed container at temperatures between 60 - 80 °F (16 - 27 °C) in a cool, well-ventilated area.

Precautions

- Review Safety Data Sheet (SDS) prior to use.
- Flammable. Keep away from fire and open flame and other possible ignition sources during storage and use. Do not smoke when using.
- Harmful or fatal if swallowed.
- Avoid prolonged inhalation.
- Avoid prolonged contact with skin. Gloves should be worn (OSHA approved).
- Avoid eye contact by wearing safety goggles with side shields.
- Thinning is not allowed.
- Do not use for splicing.
- Use only in well ventilated areas.
- Cover tightly when not in use.

LEED® Information

Post-Consumer Recycled Content: 0%

Post Industrial Recycled Content: 0%

Manufacturing Location: Akron, OH

NOTE: LEED® is a registered trademark of the U.S. Green Building Council



Typical Properties	
Properties	Typical Performance
Color	Clear
Solvents	Parachlorobenzotriflouride (PCBTF), Methyl isobutyl ketone (MIBK)
Percent Solids	21% - 24%
Viscosity	4000 - 7000 cPs #3 spindle @ 10 rpm at Room Temperature
Weight per Gallon	10.2 - 10.5 lb (4.63 - 4.76 kg)
V.O.C. Content	190 g/L

Product Packaging	
Bottle	Pint
Carton	12 pints / carton
Weight per Carton	18 lb (8.2 kg)

Please contact Holcim Technical Services at 800-428-4511 for further information.

This sheet is meant to highlight Elevate products and specifications and is subject to change without notice. Holcim takes responsibility for furnishing quality materials that meet published Elevate product specifications or other technical documents, subject to normal manufacturing tolerances. Neither Holcim nor its representatives practice architecture. Holcim offers no opinion on and expressly refuses any responsibility for the soundness of any structure. Holcim accepts no liability for structural failure or resultant damages. Consult a competent structural engineer prior to installation if the structural soundness or structural ability to properly support a planned installation is in question. No Holcim representative is authorized to vary this disclaimer.