

Technical Information Sheet



Elevate PVC Unsupported Flashing

Item Description	Item Number
1 Roll – White	W56PAW1003
1 Roll – Tan	W56PAT1003
1 Roll – Gray	W56PAG1003

Description

Elevate PVC Unsupported Flashing is a non-reinforced PVC membrane made with DuPont Elvaloy® KEE, used in roofing applications where Elevate pre-formed PVC accessory products are not appropriate. Elevate PVC Unsupported Flashing is available in 50' (15.2 m) rolls, white, tan and gray in color.

Method of Application

1. Substrates must be clean, dry, smooth, and free of sharp edges, fins, loose or foreign materials, oil, grease, and other materials that may damage the Elevate PVC Unsupported Flashing.
2. All rough surfaces that can damage the flashing shall be repaired as specified to make a smooth substrate.
3. All surface voids greater than ¼" (6.3 mm) wide shall be properly filled with an acceptable fill material.
4. Install the Elevate PVC Unsupported Flashing material with the appropriate heat welding equipment in accordance with current Elevate PVC specifications, details, and workmanship requirements.

Storage

Store material in its original unopened packaging away from direct sun light, sources of physical damage or chemical contamination.

Precautions

- Refer to Safety Data Sheets (SDS) for additional safety information.
- Exercise caution when lifting, moving, transporting storing or handling flashing rolls to avoid sources of punctures, physical damage, or chemical contamination.
- Contact a Regional Technical Coordinator at 1-800-428-4511 for specific recommendations regarding chemical or waste product compatibility with Elevate PVC Unsupported Flashing.

LEED® Information

Post-Consumer Recycled Content: 0%
 Post Industrial Recycled Content: 0%
 Manufacturing Location: Hillside, NJ
NOTE: LEED® is a registered trademark of the U.S. Green Building Council

Typical Properties		
Properties	ASTM Standard	Typical Performance
Membrane Thickness	D 751	0.055" (1.39 mm)
Tensile Strength	D 638	2,100 x 1,950 psi (14.48 x 13.44 MPa)
Elongation at Break	D 638	>250%
Tearing Strength	D 1004	12 lbf (53.38 N)
Low Temperature Bend	D 2136	-40 °F (-40 °C)
Properties After Heat Aging (Retained Values) at 176 ± 2 °F (80 ± 1 °C for 56 days ± 1 h):		
Tensile Strength	D 638	≥ 90% of original
Elongation at Break	D 638	≥ 90% of original

Product Data	
Material	DuPont Elvaloy KEE
Colors	White, Tan and Gray
Nominal Thickness	0.055" (1.39 mm)
Width	24" (610 mm)

Product Packaging	
Roll Length	50' (15.2 m)
Roll Weight	40 lb (18.2 kg)
Roll Width	24" (610 mm)
Rolls per Pallet	30
Each roll is wrapped around a core and covered with opaque poly.	

Please contact Holcim Technical Services at 800-428-4511 for further information.

This sheet is meant to highlight Elevate products and specifications and is subject to change without notice. Holcim takes responsibility for furnishing quality materials that meet published Elevate product specifications or other technical documents, subject to normal manufacturing tolerances. Neither Holcim nor its representatives practice architecture. Holcim offers no opinion on and expressly refuses any responsibility for the soundness of any structure. Holcim accepts no liability for structural failure or resultant damages. Consult a competent structural engineer prior to installation if the structural soundness or structural ability to properly support a planned installation is in question. No Holcim representative is authorized to vary this disclaimer.